

ACETex[®]

PET geotextile

Woven fabric comprised of high tenacity polyester yarns.
It can be reinforcement, separator and filtration for long-term using.

Item		Unit	Test Method	GT100/50	GT100/100	GT200/50	GT200/200	GT300/50	GT300/300	GT400/50	GT600/50	GT800/50	GT1000/50
Material				PET	PET	PET	PET	PET	PET	PET	PET	PET	PET
Mechanical Index Properties													
Nominal Tensile Strength	MD	kN/m	ISO 10319	100	100	200	200	300	300	400	600	800	1000
	CD	kN/m	ISO 10319	50	100	50	200	50	300	50	50	50	50
Elongation	MD	%	ISO 10319	10	10	10	10	10	10	10	10	10	12
Dimensional Data													
Width		m		3.8	3.8	3.8	4.5	3.8	4.5	5.0	5.0	5.0	4.5
Length		m		50	50	50	50	50	50	50	50	50	50

Note: The values given are indicative and correspond to a average results attained in our laboratories and in testing institutes. The right is reserved to make changes without notice.
Any further information needed, please contact ACE.

Accurate, Collaborative, Efficient

www.geoace.com • sales@geoace.com • TEL886-4-26595926 • FAX886-4-26595935